

Technical Services
18 Peck Avenue
P.O. Box 148
Glens Falls, NY 12801-0148

Tel 518-793-3100
Fax 518-743-3317

To: Alisa Hoffee
From: Candy Plisko
Laboratory Technician



November 4, 2002
Report: 2297-ASTRO-White 2

Request and Purpose for Analysis

Test Pactiv ASTRO-White 2 white/Bubble/Bubble/Foil for puncture resistance on each side white bubble side, and foil side.

Method of Analysis

Puncture ASTM F 1306.

Results and Data

Test indicated that foil side puncture is stronger to penetrate through than the white bubble side.

Samples ASTRO White 2	Thickness (in)	Load at Max Load (lb.)	Stress at Max Load (psi)
White Bubble side	0.2813	8.37	237.91
Foil side	0.2800	9.73	277.91